



FarrarNaturalStone

Digital Park, Station Road
Longstanton, Cambridgeshire
CB24 3FB

Commercial Sales: 01954 774762

Estimating: 01954 774760

General Enquiries: 01954 263197

Email: info@farrarnaturalstone.co.uk

Web: www.farrarnaturalstone.co.uk

Peakmoor



Technical Data

Description	Medium grained Sandstone Durable with good weathering qualities
Country of Origin	UK
Geological Type	Carboniferous, Millstone Grit
Colour	Buff/Yellow with some faint Pink/Brown Inclusions
Density	2240 kg/m ³
Compressive Strength	71.0 MPa
Water Absorption	10.49 %
Porosity	4.69 %
Durability	Tests indicates that failure due to frost action is unlikely
Flexural Strength (3 Point)	N/A
Flexural Strength (3 Point)	N/A post freeze thaw cycle
Saturation co- efficient	N/A
Slip Resistance	94 Dry / 79 Wet

Please note that stone is a natural product and all results are indicative and subject to variation.